



LUCKY BACKSHEET FOR SOLAR MODULE

Type:PPE-C2

(Transparent)

Item	Specification	Value	Method	
1	Vapor transmission rate (g/m ² · d)	≤ 1.5	ASTMF-1249	
2	Partial discharge (VDC)	> 1000	IEC60664-1:2002	
3	Breakdown voltage (KV)	> 22	ASTM D-149-97a	
4	Tensile strength (350mm/min)	MD (MPa)	≥ 110	ASTM D882-02
		TD (MPa)	≥ 110	ASTM D882-02
5	Elongation to break	MD (%)	≥ 120	ASTM D882-02
		TD (%)	≥ 100	ASTM D882-02
6	Heat shrinkage (150 °C /30min)	MD (%)	≤ 1.0	ASTM D882
		TD (%)	≤ 0.5	ASTM D882
7	EVA adhesion (N/cm)	≥ 60	GB/T8808-A	
8	Layer peel strength	≥ 5.0	GB/T8808-A	
9	Ageing-resistant performance (hour)	≥ 2000	GB/T 16422.2	
10	T.T.	≥ 88%	GB/T2680-1994	

