



Vishakha PVF

A fresh approach
to encapsulating energy



VISHAKHA[®]

SOLAR FILMS PRIVATE LIMITED
Dedicated to Innovation

Vishakha PVF is a fluoride based weather stable and UV stable back sheet. It can be used for all Crystalline PV Module Manufacturing.

S.N	Properties	UOM	Test Method	Vishakha PVF	
1	Thickness	µm	Micro meter	320	
2	Width	Mm	Scale	Up to 1250	
3	Tensile Strength	MPa	ASTM D 882	MD	100
				TD	100
4	Elongation	%	ASTM D 882	MD	≥100
				TD	≥100
5	Thermal Shrinkage @ 150 °C / 30 min	%	ASTM D 1204	MD	≤1.5
				TD	≤0.5
6	Interlayer Adhesion	N/cm	ASTM D 903	HPET-PET	≥5
				PET- Primer	≥5
7	Adhesion with EVA	N/cm	ASTM D 903	≥75	
8	MVTR	g/m ² /day	ASTM F 1249	1.69	

Construction of Vishakha PVF backsheet		
Layer No	Particulars	Thickness (µ)
1	Air side layer – PVF	25
2	Adhesive	10
3	PET	150
4	Adhesive	10
5	Cell side – VishPrime	125
Total Thickness of Back sheet		320

UL recognised under File No: QIHE2.E487880



Storage Condition : To be stored in sealed packing at temperature < 30 °C & Humidity < 60 %
 Shelf life : It is recommended to use within 12 months from the date of manufacture
 Supply : Rolls of 150 linear meter & Pallets suitable for export

VISHAKHA HOUSE, Ashirwad Paras, Corporate Road, Prahlad Nagar, Ahmedabad- 380015, Gujarat, India
 www.vishakharenewables.com Email ID: sale@vishakharenewables.com, Phone No: +91 – 7961907373 / 7069075391

The above properties are typical range of properties and not to be used for designing or establishing the limits of specifications