


**Specifications**

Nominal Voltage		12 V
Capacity (20°C)	10HR(1.80V)	200 Ah
	3HR(1.75V)	153Ah
	1HR(1.60V)	112Ah
Battery Weigh	Dry	46.5kg (102lbs)±5%
	Wet	67.5kg (148lbs)±5%
Acid Weight (d=1.24kg/l)		Approx21kg (46.2lbs)
Terminal type /material		T11 / Copper
Internal resistance (Fully charged, 25°C)		Approx. 3.5mΩ
Self-discharge	1 month	Remaining Capacity: 86%(20°C)
Nominal operating temperature		20°C±5°C (68°F±9°F)
Operating temperature range	Discharge	-15°C~50°C(5°F~122°F)
	Charge	10°C~45°C(50°F~113°F)
	Storage	10°C~30°C(50°F~86°F)
Initial charging	Constant current	Charge the battery at 0.05 C <sub>10</sub> for 72h.
	Constant voltage	Charge the battery at 0.1 C <sub>10</sub> to 2.35v/cell; then Charge the battery with 2.35v/cell until the whole charge time up to 100h.
Mark of Fully charged	Constant current	The battery voltage and density of electrolyte remain stable over 2h at the end of charging , and strong bubbles generated within the electrolyte
	Constant voltage	The charging current and density of electrolyte kept constant for more than 3h at the end of the charge; and the charging current is about 0.002~0.005 C <sub>10</sub> amp.
Supplementary charge		Charge the battery at 0.05 C <sub>10</sub> to fully charged.
Equalizing charging		Charge the battery with 2.40v/cell for 48h.
Battery operation	Float charging	Charge the battery with 2.23V (25°C); Equalizing charging the battery when the abnormal occurs
	Charge& discharge	Equalizing charging the battery after discharged and per 3months
	Backup	Supplementary charge the battery per 3 or 6 months.
Maximum charging current		50.0A
Max. discharge current		1600A(5 sec.)
Designed cycle life		1600@80% DOD (30°C)
Designed floating life		20 years(20°C)


**CHARACTERISTICS:**

- ◆ Tubular Positive Plate;
- ◆ Flooded Battery;
- ◆ Porous Rubber and Porous PVC Separator
- ◆ Transparent Container.

**Dimensions**



**Terminal**



Terminal T11

**Constant Current Discharge Characteristics (A, 25°C)**


F.V/TIME	30min	60min	2h	3h	4h	5h	6h	8h	10h	20h	24h
1.65V	161	110	66.6	52.0	41.8	36.8	31.2	23.8	20.4	11.0	9.56
1.70V	156	108	66.0	51.4	41.2	36.2	30.8	23.6	20.2	10.9	9.52
1.75V	152	105	65.0	51.0	41.0	36.0	30.6	23.4	20.2	10.9	9.46
1.80V	146	102	63.4	49.4	39.8	35.0	29.6	22.6	20.0	10.8	9.40

**Constant Power Discharge Characteristics (Watt per cell, 25°C)**


F.V/TIME	30min	60min	2h	3h	4h	5h	6h	8h	10h	20h	24h
1.65V	301	210	129	102	82.0	72.4	61.6	47.4	40.4	22.0	19.2
1.70V	291	204	127	101	81.0	71.4	60.8	46.6	40.4	21.8	19.1
1.75V	284	200	125	100	80.4	71.0	60.2	46.4	40.0	21.8	19.0
1.80V	274	194	122	97.0	78.0	68.8	58.4	45.0	39.8	21.6	18.9

Note: The above characteristics data can be obtained within three charge/discharge cycles.


Discharge Characteristics(25°C)




Initial Charging (CV) Characteristics




Effect of Temperature on Capacity




Initial Charging (CC) Characteristics(25°C)




The Relationship for Open Circuit Voltage and Residual Capacity (25°C)



Supplementary charge (CV) Characteristics



Effect of Discharge rate on Capacity



Cycle Life on D.O.D(25°C)

