

## Datasheet of Solar panel AL-frame

Grade	6063	Temper	T5	Type	Profile
Brand Name		Thickness	0.4mm-50mm	Cross-section	8mm-650mm
Surface Treatment	Customization	Alloy or Not	Is Alloy	Place of Origin	Jiangsu China
Loading port	Shanghai	Trade term	FOB CIF CNF	sample	free and fast
Advantages	1.Good quality in material; 2. Excellent surface finish 3. Competitive price				
Certificate and Standard	1) ISO9001-2008/ISO 9001:2008; 2) CQM Certification; 3) SGS, CE, BV, JIS, AS, available				
Guarantee	Surface color can be stable for 10~20 years indoor using.				
Lead Time	Mass Production: 10-20days.				
Settlement Terms	Charge by final actual weight or by drawing theoretical weight.				

### Aluminum Alloy Chemical Composition

Alloy	Element	Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti
6063	Standard	0.2-0.6	≤0.35	≤0.1	≤0.1	0.45-0.9	≤0.1	≤0.1	≤0.1
Testing result		0.483	0.143	0.019	0.017	0.554	0.0052	0.001	0.0029

