

Model	Colors	Aggregate thickness	Breadth	Structure	Thickness of each layer (Standard thickness)
Inshine201Y (1000V)	White, black	265μm (0, +5%)	≤1300mm	Air-coating//PET//EVA-coating	10μm//250μm//5μm
Inshine201H (1500V)	White, black	303μm (0, +5%)	≤1300mm	Air-coating//PET//EVA-coating	10μm//288μm//5μm
Inshine201Y-T (1000V)	Transparent	265μm (0, +5%)	≤1300mm	Air-coating//PET//EVA-coating	10μm//250μm//5μm
Inshine201H-T (1500V)	Transparent	303μm (0, +5%)	≤1300mm	Air-coating//PET//EVA-coating	10μm//288μm//5μm

Test project	Unit	Quoted standard	Specification value
Appearance	--	--	Without impurities, bubble, fold, etc.
Tensile strength	MPa	GB/T 13542.2-2009	TD ≥100 ; MD ≥100
Elongation at break	%	GB/T 13542.2-2009	TD ≥80 ; MD ≥100
Hot-shrinkage rate (150°C×30min)	%	GB/T 13542.2-2009	-0.2≤ TD ≤0.2 ; MD ≤0.6
Coating adhesion	Grade	GB/T 9286-1998	Lv. 0
Peel strength with EVA	N/cm	GB/T 2790-1995	≥60
Breakdown voltage	KV	GB/T 1408.1-2016	≥18
Partial discharge voltage	VDC	IEC 60664-1-2007	Inshine201Y: 1000V Inshine201H: 1500V
Water vapor transmittance 38°C×90%RH	g/(m ² ·day)	GB/T 26253-2010	< 2.0
Volume resistivity	Ω·cm	GB/T 31838.2-2019	≥1.0*10 ¹⁵
Reflectivity(400nm-1100nm)	%	ASTM E424-2015	≥75% (Write)
Reflectivity(780nm-1400nm)	%	ASTM E424-2015	≥60% (Black high reflex)
Light transmittance (400nm-1100nm)	%	ASTM E424-2015	≥85% (Transparent)
Boiling water treatment	Appearance detection	GB/T 17748-2008	No delamination, no foaming, no cracking
	Peel strength with		N/cm