

SOLAR SAGM 12 205

MODEL	SAGM 12 205
VOLTAGE	12
CAPACITY	205Ah @ 20Hr
MATERIAL	Polypropylene
BATTERY	VRLA AGM / Non-Spillable / Maintenance-Free
COLOR	Maroon
WATERING	No Watering Required
IEC 61427	8+ Years Life



12 VOLT

PHYSICAL SPECIFICATIONS

MODEL NAME	TERMINAL TYPE	DIMENSIONS ^B INCHES (mm)			WEIGHT F LBS. (kg)	HANDLES	INSTALLATION ORIENTATION
SAGM 12 205 M8/LT	LENGTH	WIDTH	HEIGHT ^c			Horizontal	
	14.97 (380)	6.94 (176)	14.07 (357)	122 (55)	Braided Rope	and Vertical	

ELECTRICAL SPECIFICATIONS

VOLTAGE	CAPACITY ^A AMP-HOURS (Ah)			ENERGY (kWh)	INTERNAL RESISTANCE (m Ω)	SHORT CIRCUIT CURRENT (amps)		
10	10-Hr	20-Hr	48-Hr	72-Hr	100-Hr	20-Hr	4.5	0700
12	174	205	210	213	216	2.46	4.5	2790

CHARGING INSTRUCTIONS

CHARGER VOLTAGE SETTINGS (AT 77°F/25°C)					
12V	24V	36V	48V		
20% of C ₂₀					
14.40	28.80	43.20	57.60		
13.50	27.00	40.50	54.00		
	12V 14.40	12∨ 24∨ 20% 14.40 28.80	12V 24V 36V 20% of C ₂₀ 14.40 28.80 43.20		

Do not install or charge batteries in a sealed or non-ventilated compartment. Constant under or overcharging will damage the battery and shorten its life as with any battery.

CHARGING TEMPERATURE COMPENSATION

ADD	SUBTRACT				
0.005 volt per cell for every 1°C below 25°C 0.0028 volt per cell for every 1°F below 77°F	0.005 volt per cell for every 1°C above 25°C 0.0028 volt per cell for every 1°F above 77°F				
OPERATIONAL DATA					
OPERATING TEMPERATURE	SELF DISCHARGE				


OPERATING TEMPERATURE	SELF DISCHARGE
-4°F to 122°F (-20°C to +50°C). At temperatures below 32°F (0°C) maintain a state of charge greater than 60%.	Less than 3% per month depending on storage temperature conditions.

RECYCLE RESPONSIBLY




STATE OF CHARGE MEASURE OF OPEN-CIRCUIT VOLTAGE

PERCENTAGE CHARGE	CELL	12 VOLT
100	2.14	12.84
75	2.09	12.54
50	2.04	12.24
25	1.99	11.94
0	1.94	11.64





SELF DISCHARGE VS. TIME




Storage Time in Months

BATTERY DIMENSIONS (shown with M8, height is 15.57 (395) with LT)







TERMINAL TYPE^D



E. E.

Terrinal mages are representative only. Terrinal images are representative only. Batteries in storage should be charged when they decline to 75% State of Charge (SOC). Weight may vary.

A. The amount of amp-hours (Ah) a battery can deliver when discharged at a constant rate at 86°F (30°C) for all rates and

- The anount of an privace on a dealey can derive when docutanged at a constant rule at our 1,00 of the a maintain a voltage above 1.75 V/cell. Capacities are based on peak performance. Dimensions may vary depending on type of handle or terminal. Batteries should be mounted with 0.5 inches (12.7 mm) spacing minimum.
- B



TROJAN

Designed in compliance with applicable BCI, DIN, BS and IEC standards. Tested in compliance to BCI and IEC standards.

800.423.6569 / +1.562.236.3000 / trojanbattery.com


SAGM_12_205_DS_062821

© 2021 Trojan Battery Company, LLC. All rights reserved. Trojan Battery Company is not liable for damages that may result from any information provided in or omitted from this publication, under any circumstances. Trojan Battery Company reserves the right to make adjustments to this publication at any time, without notice or obligation.

140 60 120 50 40 100 30 80 £ Û 20 60 Temperature Temperature 10 40 0 20 -10 0 -20 -20 -30 -40 -40 20% 609 809 100% 120% 0% 40% Percent of Available Capacity

PERCENT CAPACITY VS. TEMPERATURE

TROJAN SAGM 12 205 PERFORMANCE



Current (Amps)