

## A Reliable Power Solution Provider

# Lithium Iron Phosphate (LiFePO<sub>4</sub>) Battery

## AJ-LFP12.8V84AH


#### Features

- ◆ Using the technology of lithium iron phosphate cell, superior safety, thousands of cycles, 100%DOD, under normal conditions
- ◆ Built-in automatic protection for over-charge, over discharge, over current and over temperature
- Maintenance free
- ◆ Internal cell balancing
- ◆ Lighter weight: About 40% ~50% of the weight of a comparable lead acid battery.
- ◆ Can be charged using most standard lead-acid charges (set)
- ◆ Wider temperature range:-20°C~60°C

#### **Application**

- ◆ UPS
- Solar &Wind power system
- Golf Cart
- ◆ Electric vehicle , E-bike, E-rickshaw e.g.
- Lighting





General Specification		
Electrical Characteristics	Nominal Voltage	12.8V
	Nominal Capacity	84Ah@0.2C
	Energy	1075.2Wh
	Internal Resistance	≤45mΩ
	Cycle Life	>2000 Cycles @ 0.2C Charge/Discharge at 100%DOD,End of Life 70% Capacity.
	Months Self Discharge	≤3.5% per month at 25°C
Standard Charge	Charge Voltage	(14.6±0.2) V
	Charge Mode (CC/CV)	At $0^{\circ}$ C ~45 $^{\circ}$ C temperature, charged to 14.6V at a constant current of $0.2C_5A$ , and then,changed continuously with constant voltage of 14.6V until the current was not more than $0.02C_5A$ .
	Charger Current	16.8A
	Max.Charge Current	42A
Standard Discharge	Discharge Current	16.8A
	Max. Continuous Current	84A
	Max.Pulse Current	120A(<3S)
	Discharge Cut-off Voltage	10.0V
Environmental	Charge Temperature	0°C to 45°C (32°F to 113°F) @60±25% Relative Humidity
	Discharge Temperature	-20°C to 60°C (-4°F to 140°F) @60±25% Relative Humidity
	Storage Temperature	0°C to 45°C (32°F to 113°F) @60±25% Relative Humidity
	Water Dust Resistance	IP55
Mechanical	Cell & Method	IFR32700 N60,4S14P
	Plastic Case	ABS
	Dimension(L*W*H*TH)	(260*169*213*218) mm
	Weight	Approx. 10.2Kg
	Terminal	M8


AJ Power Co., Ltd.


Add.:Room 305,level 3,No.1 of Shiwaitaoyuan Building,East Guangshen Road,Xixiang,Baoan District,Shenzhen,Guangdong,China.

# Lithium Iron Phosphate (LiFePO<sub>4</sub>) Battery


## AJ-LFP12.8V84AH

#### Different Rate Discharge Curve @ 25°0







## Charge Characteristics @0.2C&0.5C, 25°C




Charge Characteristics @0.2C&0.5C, 25°



## Different DOD Discharge Cycle Life Curve @0.5C, 25 $^\circ$ C



### Open circuit voltage VS SOC%



AJ Power Co., Ltd.

Add.:Room 305,level 3,No.1 of Shiwaitaoyuan Building,East Guangshen Road,Xixiang,Baoan District,Shenzhen,Guangdong,China