

Yparex® 0F0023

Technical data sheet

Property data

Yparex Polyolefin Elastomer Encapsulant Film - Transparent

Visit us at www.yparex.com

Version 1.7, issue date 3-5-2021

Properties	Typical Data	Unit	Test Method
Film dimensions			
Thickness after lamination	460	µm	
Weight/area	406	g/m ²	
Width	1060	mm	
Length	150	m	
Diameter	310	mm	
Inner core diameter	76,5	mm	
Outer core diameter	91	mm	
Weight	65	kg	

Film characteristics

Electrical property			ASTM D257
Volume resistivity (40 % RH, 23 °C)	1,57E+15	Ω.cm	
Light transmission			
UV cutoff	362	nm	
500 nm	92,1	%T	
Average 380-1100 nm	92,5	%T	
Water Vapor Transmission Rate			ISO 15106-3
WVTR - uncured (100 % RH, 25 °C)	2,11	g/(m ² .day)	
Adhesion to glass			
180 ° peel (1 mm/sec)	> 100	N/cm	

Processing recommendations for optimal crosslinking and adhesion

Lamination temperature	145-150	°C
Lamination time	15-20	min
Vacuüm		

All information supplied by or on behalf of Yparex BV in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but Yparex BV assumes no liability and makes no warranties of any kind, explicitly or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the aforementioned information or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequence from the use of all such information. Typical values are indicative only and are not to be construed as being binding specifications.